

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08L 23/02 // (C08L 23/02, 71:02)	A1	(11) International Publication Number: WO 99/65981 (43) International Publication Date: 23 December 1999 (23.12.99)
(21) International Application Number: PCT/US99/12530 (22) International Filing Date: 4 June 1999 (04.06.99) (30) Priority Data: 09/094,766 15 June 1998 (15.06.98) US (71) Applicant: KIMBERLY-CLARK WORLDWIDE, INC. [US/US]; 401 North Lake Street, Neenah, WI 54956 (US). (72) Inventors: WANG, James, H.; 1325 East Overland Road, Appleton, WI 54915 (US). SCHERTZ, David, Michael; 135 Taylor Ridge Court, Rosewell, GA 30076 (US). (74) Agents: WILHELM, Thomas, D.; Wilhelm Law Service, S.C., 3rd floor, 100 West Lawrence Street, Appleton, WI 54911 (US) et al.		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: WATER-MODIFIABLE FLUSHABLE POLYOLEFIN-CONTAINING FILM AND ARTICLE MADE THEREFROM (57) Abstract The invention provides a water degradable polyolefin-containing film having greater than about 55 weight percent of a polyolefin and less than about 45 weight percent of poly(ethylene oxide) of weight average molecular weight of less than about 100,000. Preferably, the polyolefin is low density polyethylene. The polyolefin-containing film, when immersed in water for about 30 seconds, loses at least 10 % in two or more of the tensile properties: percent strain-to-break, peak stress, energy-to-break and modulus when compared to the dry or pre-immersion values. Also provided are flushable personal care articles such as infant diapers, feminine hygiene napkins, and adult incontinence garments having a backing or barrier layer comprising a water degradable polyolefin-containing film of the invention.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

WATER-MODIFIABLE FLUSHABLE POLYOLEFIN-CONTAINING FILM
AND ARTICLE MADE THEREFROM

Field of the Invention

5 The present invention relates to a water-degradable or flushable polyolefin-containing film. More particularly, the present invention relates to a water-degradable or flushable polyolefin-containing film having greater than about 55 weight percent of a polyolefin and less than about 45 weight percent of poly(ethylene oxide).

Background of the Invention

15 Personal care products, such as infant diapers, sanitary napkins, adult incontinence garments, and the like are generally constructed from a number of different components and materials. Such articles typically have some portion, usually the backing layer, liner, barrier or baffle constructed of a liquid repellent film material. This repellent material is

20 appropriately constructed to minimize or prevent the exudation of the absorbed liquid from the article and to obtain greater utilization of the absorbent capacity of the product. Liquid repellent films commonly used includes plastic materials such as polyethylene films and the like.

25 Although such products are relatively inexpensive, sanitary and easy to use, disposal of a soiled product is not without its problems. With greater interest being placed in protecting the environment, there is a need to develop materials that are more compatible with the existing and developing waste disposal technologies while still delivering the performance consumers

30 have come to expect. An ideal disposal alternative would be to use municipal sewage treatment and private residential septic systems. Products suited for disposal in sewage systems can be

flushed down a convenient toilet and are termed "flushable."

While flushing such articles would be convenient, the liquid repellent material which normally does not disintegrate in water tends to plug toilets and sewer pipes. It therefore becomes necessary, although undesirable, to separate the barrier film material from the absorbent article prior to flushing.

In addition to the article itself, typically the packaging in which the disposable article is distributed is also made from a water resistant material. Water resistivity is necessary to prevent the degradation of the packaging from environmental conditions and to protect the disposable articles therein. Although this packaging may be safely stored with other refuse for commercial disposal, and especially in the case of individual packaging of the products, it is often more convenient to dispose of the packaging in the toilet with the discarded disposable article. However, in the cases where such packaging is composed of a water resistant material, plugging of the drains to the toilet typically results.

Desirably, a commercial, water degradable or flushable product should be relatively responsive to water and be transportable in a sewer system. Commercially available water-soluble polymers, such as poly(ethylene oxide) (PEO), poly(vinyl alcohol) (PVOH), acrylamide polymers, acrylic acid-based polymers, and cellulose derivatives, possess the desired characteristics for flushability, such as water solubility and/or water dispersibility. However, due to their in-use degradability and storage degradation, these materials function poorly as components in personal care products. Other disadvantages are that these polymers are difficult to process and are substantially more expensive than polyolefins.

The requirements for a functional and flushable product provide a substantial challenge in finding suitable materials with the desired properties. In an attempt to overcome the flushability problem of a water resistant film the prior art has

modified the water resistant polymer. One of the more useful ways of modifying polymers involves blending them with other polymers of different structures and properties.

Polymer blends of polyolefins and poly(ethylene oxide) have
5 been shown to be water modifiable at expectedly low weight %
polyolefin levels. Such blends would be anticipated to be
flushable when exposed to water in a toilet but do not possess
the dry mechanical properties required for functionality in use.
Moreover, the high content of poly(ethylene oxide) makes such
10 materials prohibitively expensive for use in a disposable
personal hygiene article such as a sanitary napkin, diaper and
the like. Polymer blends of polyolefins and poly(ethylene
oxide) containing greater than about 45 weight percent of
polyolefin are generally water resistant and are not water
15 modifiable. In view of the problems of the prior art, it
remains highly desirable to provide a water modifiable film
having a substantial portion of thereof composed of a
polyolefin. More desirably, the water modifiable film should
have greater than about 55 weight percent of a polyolefin. When
20 dry, the film should have the mechanical properties necessary
for functionality. When wet, the film should lose at least a
portion of its mechanical properties which would render the film
flushable and transportable in a sewer system. Such films could
be used for making flushable barrier films for personal care
25 products.

It is therefore an object of the invention to provide a
polyolefin-containing film that is water modifiable or water-
degradable which contains higher levels of polyolefin content.
More specifically, it is an object of the invention to provide a
30 polyolefin-containing film having greater than about 55 weight
percent of a polyolefin and less than about 45 weight percent of
poly(ethylene oxide) that is water-modifiable or water
degradable.

Summary of the Invention

In its principal embodiment, the present invention provides a water degradable polyolefin-containing film comprising
5 greater than about 55 weight percent of a polyolefin and less than about 45 weight percent of poly(ethylene oxide) wherein the poly(ethylene oxide) has a weight average molecular weight of less than about 100,000. The film of the invention has a loss
10 of at least 10% in two or more tensile properties selected from percent strain-to-break, peak stress, energy-to-break and modulus after being immersed in water for 30 seconds.

In an alternative embodiment, the present invention provides a flushable personal care article having a backing or barrier film comprising greater than about 55 weight percent of
15 a polyolefin and less than about 45 weight percent of poly(ethylene oxide) wherein the poly(ethylene oxide) has a molecular weight of less than about 100,000. The film of the invention has a loss of at least 10% in two or more tensile properties selected from percent strain-to-break, peak stress,
20 energy-to-break and modulus after being immersed in water for 30 seconds.

Detailed Description of the Invention

As used herein "water modifiable" or "water degradable"
25 means that a four mil thick film (one mil equals 0.001 of an inch or 0.025 mm), when immersed in water for 30 seconds, will have modified by greater than 10% two or more of the following tensile properties: percent strain-to-break, peak stress, energy-to-break, and modulus. To determine the degree of
30 modification, the "wet" values are compared to the pre-immersed or "dry" film values.

The term "personal care product" or "personal care article" means articles such as infant diapers, sanitary napkins, adult incontinence garments, and the like.

By the term "backing layer" or "barrier layer" is meant that component of an infant diaper, sanitary napkin, adult incontinence garment or the like which is worn during normal use furthest from the user's body and which serves to minimize or prevent the exudation of the absorbed liquid.

Although the present invention is described with reference to a water modifiable film and, in particular, to personal care articles having a backing layer, liner, or barrier layer comprising such films, one skilled in the art will understand that the composition of the invention can be used to make other thermoplastic articles that can be extruded or injection molded in which the desired property of water degradability is needed, such as packaging articles and the like.

In one embodiment of the invention, the water modifiable or water-degradable film comprises greater than about 55 weight percent of a polyolefin and less than about 45 weight percent of poly(ethylene oxide). Desirably, the water-modifiable film comprises from about 55 weight percent to about 85 weight percent of a polyolefin and from about 45 weight percent to about 15 weight percent of poly(ethylene oxide). More desirably, the water modifiable film comprises from about 65 weight percent to about 85 weight percent of a polyolefin and from about 35 weight percent to about 15 weight percent of poly(ethylene oxide). The poly(ethylene oxide) useful in making the film has a weight average molecular weight of less than about 100,000. The preferred polyolefin is polyethylene, with low density polyethylene ("LDPE") being particularly preferred.

The saturated ethylene polymers useful in the practice of this invention are homopolymers of ethylene, preferably low density polyethylene, and are essentially linear in structure. As used herein, the term "saturated" refers to polymers which are fully saturated, but also includes polymers containing up to about 5% unsaturation.

Low density polyethylene suitable for use in the films of

this invention has a density of less than 0.94 g/cc and are usually in the range of 0.91 g/cc to about 0.93 g/cc. Low density polyethylene has a melt index ranging from about 0.05 dg/min to about 100 dg/min and desirably from 0.05 dg/min to about 20 dg/min. Ultra low density polyethylene also can be used in accordance with the present invention. Generally, ultra low density polyethylene has a density of less than 0.90g/cc.

A suitable commercially available low density polyethylene material for use in the polymer film blends of the present invention is LDPE 501I available from Dow Plastics Division of Dow Chemical Co., Midland, MI. The resin has a density of 0.922 g/cm³ and a melt index of 1.9 dg/min.

A suitable low molecular weight poly(ethylene oxide) for use in the polymer blends of the present invention is available from Union Carbide Corporation, Danbury, CT under the trade name of POLYOX® Grade WSN-10 having a weight average molecular weight of 100,000. Typically, poly(ethylene oxide) is a dry free flowing white powder having a crystalline melting point in the order of about 650C, above which poly(ethylene oxide) resin becomes thermoplastic and can be formed by molding, extrusion and other methods known in the art.

The water-modifiable or water degradable polyolefin-containing films of the present invention, when immersed in water for about 30 seconds, lose greater than 10% in at least two of the tensile properties: percent stain-to-break, peak stress, energy-to break and modulus. Typically, at least two of the tensile properties will be reduced greater than about 25%, more typically, by about 25% to about 98%, and even more typically by at least about 30% to about 80%. The values in determining the extent of loss of the tensile property or properties modification are relative to the dry condition, i.e. pre-immersion value for that measured property.

The present invention is illustrated in greater detail by the specific examples presented below. It is to be understood

that these examples are illustrative embodiments and are not intended to be limiting of the invention, but rather are to be construed broadly within the scope and content of the appended claims.

5

Comparative Example A

A 60/40 weight percent blend of low density polyethylene (PE) having a melt index of 1.9 decigrams per minute (dg/min) and a density of 0.922 grams per cubic centimeter (g/cc) (Dow 10 503I; available from Dow Chemical Company, Midland, MI) and poly(ethylene oxide) (PEO) having a molecular weight of 200,000 g/mol (POLYOX® WSRN-80 available from Union Carbide Corp., Danbury, CT) was fed to a Haake counter-rotating twin screw extruder at a rate of 5 lb/hr (2.27 kg/hr). The extruder had a 15 length of 300 millimeters. Each conical screw had 30 millimeters diameter at the feed port and a diameter of 20 millimeters at the die. The extruder had four heating zones set at 170°C, 180°C, 180°C and 190°C. The screw speed of the extruder was 150 rpm.

20 Film processing of all the blends was performed using a Haake extruder counter-rotating twin screw extruder as described above with the following modifications. The extruder included a 4 inch (101.6 mm) slit die at a temperature of 195°C. The screw speed was at 30 rpm. A chilled wind-up roll was used to collect 25 the film. The chilled roll was operated at a speed sufficient to form a film having a thickness of about 4 mils (about 0.102 mm) and was maintained at a temperature of 15-20°C. Dry tensile tests were performed on a Sintech 1/D tensile tester available from MTS Systems Corp., Machesny Park, IL. The film was cut 30 into a type V dogbone shape in accordance with ASTM D638. The test was performed with a grip separation of 30 millimeters and a crosshead speed of 4 millimeters/second.

Wet tensile tests were performed on a Vitrodyne V1000 mini-tensile tester available from Chatillon, Greensboro, NC. The

film samples were placed in the grips and the testing apparatus was submerged in ambient temperature, non-stirred water for 30 seconds. The test was then run under the same conditions as the dry tensile test. Peak stress, percent strain-to-break, energy-to-break (as area under stress versus strain curve) and modulus were calculated using the actual stress versus strain values recorded from the tensile tester for each dry or wet tensile test. The peak stress was recorded as the greatest stress value. The percent stain-to-break was recorded as the percent strain value at break. The energy-to-break (area under stress versus stain curve) was calculated by the summation of rectangular "slices" under the curve determined for each strain value recorded from the tensile test, using the following formula:

$$((\text{Strain value}_x - \text{Strain value}_{x-1}) \times (\text{Stress value}_x + \text{Stress value}_{x-1}))/2$$

where 'X' is the sequential number of the slice. The modulus was calculated by linear regression of the initial region of the stress versus strain curve. The dry and wet properties of the film produced from the blend in Comparative Example A are indicated in Table 1 below.

Table 1
Percent Loss in Tensile Properties

Comparative Example A			
Property	Dry	Wet	Percent Loss from Dry to Wet
Thickness (mil)	4.1	4.2	
Percent Strain	550	500	9
Peak Stress (MPa)	16.6	16.2	2
Energy-to-Break (x 10 ⁶ J/m ³)	65.7	64.0	3
Modulus	77.0	62.3	19

This example shows that a polymer blend of low density

polyethylene with poly(ethylene oxide) having a weight average molecular weight of 200,000 is water resistant. The polymer blend was not water modifiable after 30 seconds of immersion in water.

Example 1

In Example 1, a Werner & Pfleiderer ZSK-30 extruder (available from Werner & Pfleiderer, Ramsey, New Jersey) was used. The extruder had a pair of co-rotating screws arranged in parallel. The center distance between the two shafts was 26.2 mm. The nominal screw diameter was 30 mm. The actual outer screw diameter was 30 mm. The inner screw diameter was 21.3 mm. The thread depth was 4.7 mm. The extruder had 14 processing barrels, with 13 heated barrels divided into 7 heating zones. The overall processing length was 1340 mm.

A 60/40 weight percent resin blend of low density polyethylene (Dow 503I) and poly(ethylene oxide) having a weight average molecular weight of about 100,000 g/mol (Union Carbide POLYOX® WSRN-10) was fed to the ZSK-30 extruder at a rate of 35 lb/hr (15.91 kg/hr). The seven heating zones were all set at 180° C. The screw speed was 300 rpm.

The dry and wet properties of the film produced from the blend in Example 1 are indicated in Table 2 below.

Table 2
Percent Loss in Tensile Properties

Example 1			
Property	Dry	Wet	Percent Loss from Dry to Wet
Thickness (mil)	3.2	3.2	
Percent Strain	717	100	86
Peak Stress (MPa)	11.3	3.6	68
Energy-to-Break (x 10 ⁶ J/m ³)	65.8	2.7	96
Modulus (Mpa)	96.0	27.2	72

In accordance with the invention, Example 1 was a film of a polymer blend of 60 weight percent of an unmodified polyethylene and 40 weight percent an unmodified poly-(ethylene oxide) having a weight average molecular weight of about 100,000. The film of this polymer blend was water degraded after 30 seconds of submersion in water as shown by the data showing percent loss tensile properties of greater than 68% from dry to wet in all properties tested and greater than 86% loss in percent strain and energy-to-break.

While the invention has been described with reference to the preferred embodiments and illustrated with regard to a range of optional features, those skilled in the art will appreciate that various substitutions, omissions, changes and modifications may be made without departing from the spirit of the invention as it is defined by the appended claims. Accordingly, it is intended that the foregoing description be deemed merely exemplary of the preferred scope of the present invention and not be deemed a limitation thereof.

WE CLAIM:

- 1 . A water degradable polyolefin-containing film comprising greater than about 55 weight percent of a polyolefin and less than about 45 weight percent of poly(ethylene oxide) wherein said poly(ethylene oxide) has a molecular weight of less than about 100,000, said film having a loss of at least 10% in two or more tensile properties selected from percent strain-to-break, peak stress, energy-to-break and modulus after being immersed in water for 30 seconds.
2. A film according to Claim 1 wherein said film comprises from about 55 weight percent to about 85 weight percent of a polyolefin and from about 45 weight percent to about 15 weight percent of poly(ethylene oxide).
3. A film according to Claim 1 wherein said film comprises from about 65 weight percent to about 85 weight percent of a polyolefin and from about 35 weight percent to about 15 weight percent of poly(ethylene oxide).
4. A film according to Claim 1 wherein said polyolefin is low density polyethylene.
5. A film according to Claim 2 wherein said polyolefin is low density polyethylene.
6. A film according to Claim 3 wherein said polyolefin is low density polyethylene.
7. A film according to Claim 1 wherein said loss in two or more of the tensile properties is greater than 25% after being immersed in water for 30 seconds.

8. A film according to Claim 7 wherein said loss in two or more of the tensile properties is from about 25% to about 98% after being immersed in water for 30 seconds.
9. A film according to Claim 8 wherein said loss in two or more of the tensile properties is from about 25% to about 98% after being immersed in water for 30 seconds.
10. A film according to Claim 9 wherein said loss in two or more of the tensile properties is from about 25% to about 98% after being immersed in water for 30 seconds.
11. A film according to Claim 7 wherein said loss in two or more of the tensile properties is from about 30% to about 80% after being immersed in water for 30 seconds.
12. A film according to Claim 8 wherein said loss in two or more of the tensile properties is from about 30% to about 80% after being immersed in water for 30 seconds.
13. A film according to Claim 9 wherein said loss in two or more of the tensile properties is from about 30% to about 80% after being immersed in water for 30 seconds.
14. A polyolefin-containing film comprising greater than about 60 weight percent of low density polyethylene and about 40 weight percent of poly(ethylene oxide), wherein said poly(ethylene oxide) has a weight average molecular weight of less than about 100,000, said film having a loss of at least 10% in at least two tensile properties selected from percent strain-to-break, peak stress, energy-to-break and modulus after being immersed in water for 30 seconds.

15. A water-degradable personal care article having a backing or barrier layer comprising a polyolefin-containing film comprising greater than about 55 weight percent of low density polyethylene and less than about 45 weight percent of poly(ethylene oxide), wherein said poly(ethylene oxide) has a weight average molecular weight of less than about 100,000, said film having a loss of at least 60% in at least two tensile properties selected from percent strain-to-break, peak stress, energy-to-break and modulus after being immersed in water for 30 seconds.

16. A personal care article according to Claim 18 wherein said backing or barrier layer comprises about 60 weight percent low density polyethylene and about 40 weight percent poly(ethylene oxide), wherein said poly(ethylene oxide) has a weight average molecular weight of less than about 100,000.

17. A personal care article according to Claim 18 wherein said article is a feminine hygiene napkin.

18. A personal care article according to Claim 18 wherein said article is an infant diaper.

19. A personal care article according to Claim 18 wherein said article is an adult incontinence garment.

INTERNATIONAL SEARCH REPORT

International Application No
PC1/US 99/12530

A. CLASSIFICATION OF SUBJECT MATTER IPC 6 C08L23/02 //(C08L23/02,71:02)		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 6 C08L		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	WO 98 29502 A (KIMBERLY CLARK CO) 9 July 1998 (1998-07-09) abstract; claims 1-11 page 2, line 22 - line 25 ---	1-19
E	WO 99 34049 A (KIMBERLY CLARK CO) 8 July 1999 (1999-07-08) abstract; claims 1-15 page 5, line 24 - line 26 page 8, line 28 - line 32 page 12, line 10,11 ---	1-19
A	WO 98 10928 A (KELLY PETER YATES ;DU PONT CANADA (CA)) 19 March 1998 (1998-03-19) claims 4,6; example 1 page 5, line 5 - line 10 page 5, line 27 - line 28 ---	1-19
-/--		
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents : "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "A" document member of the same patent family		
Date of the actual completion of the international search 23 September 1999		Date of mailing of the international search report 01/10/1999
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer Bergmans, K

INTERNATIONAL SEARCH REPORT

International Application No

PC1/US 99/12530

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 296 355 A (UNION CARBIDE CORP) 28 December 1988 (1988-12-28) abstract; claim 1 ----	1-16
A	US 4 415 691 A (ALLEN JAMES A ET AL) 15 November 1983 (1983-11-15) abstract; claims 1,9,10 ----	1-16
A	US 5 464 687 A (SHETH PARESH J) 7 November 1995 (1995-11-07) claims 11,7 -----	1-16

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/12530

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9829502 A	09-07-1998	AU 5618698 A	31-07-1998
WO 9934049 A	08-07-1999	NONE	
WO 9810928 A	19-03-1998	AU 4292597 A	02-04-1998
EP 0296355 A	28-12-1988	US 4812505 A	14-03-1989
		AT 130021 T	15-11-1995
		AU 601581 B	13-09-1990
		AU 1633988 A	24-11-1988
		CA 1326085 A	11-01-1994
		DE 3854659 D	14-12-1995
		DE 3854659 T	30-05-1996
		ES 2080045 T	01-02-1996
		GR 3018045 T	29-02-1996
		JP 1033145 A	03-02-1989
		JP 8006023 B	24-01-1989
US 4415691 A	15-11-1983	US 4327009 A	27-04-1982
US 5464687 A	07-11-1995	US 5468259 A	21-11-1995
		AU 695499 B	13-08-1998
		AU 2827295 A	09-02-1996
		BR 9508277 A	28-10-1997
		CA 2194238 A	25-01-1996
		CN 1157642 A	20-08-1997
		EP 0770152 A	02-05-1997
		JP 10502687 T	10-03-1998
		WO 9601916 A	25-01-1996
		US 5614574 A	25-03-1997
		US 5550192 A	27-08-1995